

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
17 February 2005 (17.02.2005)

PCT

(10) International Publication Number  
**WO 2005/014713 A1**

(51) International Patent Classification<sup>7</sup>: C08L 23/10.  
C08J 5/18, B32B 27/32

(21) International Application Number:  
PCT/EP2004/008252

(22) International Filing Date: 22 July 2004 (22.07.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
03017824.8 5 August 2003 (05.08.2003) EP  
60/497,830 26 August 2003 (26.08.2003) US

(71) Applicant (for all designated States except US): BASELL  
POLIOLEFINE ITALIA S.p.A. [IT/IT]; Via Pergolesi  
25, I-20124 Milano (IT).

(72) Inventors; and

(75) Inventors/Applicants (for US only): DE PALO, Roberto  
[IT/IT]; Via Pesci, 158, I-44100 Ferrara (IT). MASSARI,  
Paola [IT/IT]; Via E. Farolfi, 3, I-44100 Ferrara (IT).  
CAGNANI, Camillo [IT/IT]; Via del Castelluccio 15,  
I-44100 Ferrara (IT).

(74) Agent: COLUCCI, Giuseppe; Basell Poliolefine Italia  
S.p.A., Intellectual Property, P.le G. Donegani, 12, I-44100  
Ferrara (IT).

(81) Designated States (unless otherwise indicated, for every  
kind of national protection available): AE, AG, AI, AM,  
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,  
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,  
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,  
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,  
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,  
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,  
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,  
ZW.

(84) Designated States (unless otherwise indicated, for every  
kind of regional protection available): ARIPO (BW, GH,  
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,  
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,  
FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,  
SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,  
GW, ML, MR, NE, SN, TD, TG).

**Declaration under Rule 4.17:**

— of inventorship (Rule 4.17(iv)) for US only

**Published:**

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: POLYOLEFIN ARTICLES

(57) Abstract: Articles, in particular non-pressure mono- or multi-layer pipes, prepared by extrusion, moulding and combination thereof, comprising a heterophasic polyolefin composition comprising (1) 65-95% of a crystalline propylene polymer insoluble in xylene at ambient temperature in an amount over 85% and having a polydispersity index ranging from 4 to 13 and an intrinsic viscosity value ( $[\eta]_1$ ) of over 2.2 dl/g. and (2) 5-35% of an elastomeric olefin polymer of ethylene with a C<sub>3</sub>-C<sub>10</sub>  $\alpha$ -olefin having an ethylene content ranging from 15 to 85% and an intrinsic viscosity value ( $[\eta]_2$ ) of at least 1.4 g/ml. The  $[\eta]_1/[\eta]_2$  ratio ranging from 0.45 to 1.6. The articles typically have modulus of elasticity in tension higher than 2000 MPa. The invention also relates to the said heterophasic polyolefin composition and an extrusion process for producing the said articles.

WO 2005/014713 A1